

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C04B 35/66, 35/14, 38/08, 41/45	A1	(11) International Publication Number: WO 99/65842 (43) International Publication Date: 23 December 1999 (23.12.99)
(21) International Application Number: PCT/BE99/00073 (22) International Filing Date: 7 June 1999 (07.06.99) (30) Priority Data: 987608 15 June 1998 (15.06.98) FR (71) Applicant (for all designated States except US): VESUVIUS CRUCIBLE COMPANY [US/US]; Suite 200, 103 Foulk Road, Wilmington, DE 19803 (US). (71) Applicant (for MG only): VESUVIUS GROUP S.A. [BE/BE]; Avenue du Commerce 40, B-1420 Braine-l'Alleud (BE). (72) Inventor; and (75) Inventor/Applicant (for US only): BRANDY, Gilbert [FR/FR]; Rue Louis Bréguet 24, F-59600 Maubeuge (FR). (74) Agent: DEBLED, Thierry; Vesuvius Group S.A., Intellectual Property Dept., Rue de Douvrain 17, B-7011 Ghlin (BE).	(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>	
(54) Title: INSULATING REFRACTORY MATERIAL (57) Abstract The invention concerns an insulating refractory material comprised of 20-80 % by weight of a ceramic matrix, 5-40 % by weight of insulating microspheres, 0.5-15 % by weight of one or more binders and 0-5 % by weight of water. The ceramic matrix is comprised of vitreous grains, notably atomized silica. It also contains 0.5-4 % by weight of a deflocculant and 0.5-4 % by weight of colloidal silica. The insulating microspheres are hollow spheres of a material based on silica and alumina. They contain 55-65 % by weight of silica and 27-33 % by weight of alumina.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

INSULATING REFRACTORY MATERIAL.**Description.**

Insulating refractory materials are used in industry, notably in metallurgy, for reducing heat losses and for saving energy. These materials can also be used for coating an article. They can also be used for producing an insulating component in the material itself. They can also
5 be used to produce elements such as panels or bricks that will be used severally to form an insulating unit.

For example, refractory material components are used in the continuous casting of steel for the transfer of molten steel between various containers, notably between the ladle and the distributor, and the continuous casting mold. These components should be made more
10 insulating thermally to improve the preheating efficiency (when the components are preheated), to avoid solidification of the steel on the inside walls of the taphole and, in the case of pouring components used for a distributor, to avoid bridging between the casting component and the mold walls.

According to another example, to improve the preheating efficiency of the distributor stopper rods, a sleeve of insulating refractory material that is fitted on the stopper rod and retains the
15 heat of the burner is used.

It is customary to use sheets or mats of paper impregnated with ceramic fibers as the insulating refractory material. This material guarantees a good quality of the thermal insulation, but presents several shortcomings.

20 The placement of the ceramic paper requires operations of cutting, placement and gluing that are long and tedious. Furthermore, the handling of sheets or plates of ceramic paper permits the escape of carcinogenic ceramic fibers that can be inhaled by the operators.

An insulating refractory coating for steel casting components is also known (EP 0 296 981). This coating is obtained from a composition of an aqueous suspension containing 30-85 % by
25 weight of a finely divided constituent such as fused silica, alumina or zirconia powders and alumina beads, a ceramic charge of fibers of alumina silica, zirconia, titanium dioxide or chrome-alumina, or even alumina or zirconia beads. This composition is also comprised of up to 7 % by weight of a binder such as sodium hexametaphosphate or sodium silicate, and up to 40 % by weight of glass generating frit.

30 Such a coating avoids some of the disadvantages of plates of ceramic paper impregnated with ceramic fibers. In particular, it is more rapid to install because it does not require a large number of operations. In addition, it can facilitate avoiding the presence of ceramic fibers that are dangerous for the health of the operators. However, it presents certain disadvantages. Its thermal insulation characteristics are not very good due to its low porosity
35 (ca. 20 %). This porosity is essentially open, which assures less good thermal insulation characteristics than a closed porosity. Furthermore, it is difficult to deposit a substantial thickness of coating on a casting. To increase the thickness of the coating, it is necessary to preheat the components before coating them, which requires a supplementary stage and implies a supplementary cost. Furthermore, after having deposited a first layer, it is not

possible to deposit a second layer because the outer surface of the coating is smooth and impermeable, which does not permit a good adhesion of the second layer.

The object of the present invention is an insulating refractory material that remedies these

- 5 shortcomings. This insulating refractory material is comprised of 20-80 % by weight of a ceramic matrix, 5-40 % by weight of insulating microspheres, 0.5-15 % by weight of one or more binders and up to 5 % by weight of water. The matrix can be a matrix of vitreous grains, notably silica, preferably atomized silica; it may also comprises non-vitreous grains such as alumina or magnesia. Preferably, the matrix does not comprise more than 30 % by weight of the matrix of
- 10 non-vitreous grains.

- USP 4,874,726 discloses a refractory material having a high abrasion resistance and a relatively low thermal conductivity. This material comprises from 40 to 95 % by weight of vitreous silica, up to 25 % by weight of a calcined refractory aggregate and the balance of a calcium aluminate cement (binder). For each 100 parts of this mix, the material further comprises from 3 to 15 % by
- 15 weight of alumina-silica based microspheres. This composition intended for the formation of refractory pieces by casting or gunning, has a viscosity, when mixed with the appropriate amount of water, of about 4 to about 6 Pa.s. This extremely low viscosity, usual for the formation of refractory pieces by casting operations, is not compatible with the formation of a coating by immersion.

- 20 The material can also have up to 4 % by weight of a deflocculant and up to 20 % by weight of colloidal silica. Preferably, it has from 0.5 to 4 % by weight of a deflocculant and from 0.5 to 20 % by weight of colloidal silica

The insulating microspheres may be hollow spheres of a material based on silica and alumina. This material contains 55-65 % by weight of silica and 27-33 % by weight of alumina.

- 25 The main characteristic of the binder of the invention is that it must confers to the aqueous composition (i.e. the slip) used in making the refractory material of the invention, a viscosity compatible with the formation of a coating by dipping or immersing the refractory piece into said slip. The formation of a regular and homogeneous coating depends indeed largely upon the viscosity of the slip. A suitable viscosity is generally higher than 8 Pa.s and preferably higher than
- 30 10 Pa.s.

Binders that might be used according to the invention are clays of the kaolinite type and organic binders such as the polysaccharides (e.g., dextrine).

These binders confer to the aqueous composition a viscosity which perfectly fulfills the above discussed requirements.

- 35 The invention also concerns a component, notably for casting steel, having a body of refractory material coated with the insulating material of the invention. The component can also be a composite piece produced partially of the material of the invention. This component can be produced, e.g., cast, in a single operation or formed of several assembled pieces.

- The invention also concerns a process for preparing a composition for effecting an insulating
- 40 coating or making an insulating piece.

According to this process:

- one or more binders are dissolved in a quantity of water;

- a deflocculant is added;
 - grains of atomized vitreous silica are added while agitating the solution to hydrate them and form a slip;
 - microspheres of an insulating material are added while continuing to agitate the slip
- 5 to keep it homogeneous.

In a preferred variant of the process, colloidal silica is added after the deflocculant.

The composition used in making the material can be a slip containing from 20 to 70 % by weight of atomized vitreous silica grains, from 5 to 40 % by weight of insulating microspheres, from 0.5 to 20 % by weight of one or more binders and from 5 to 25 % by weight of water. It may further comprises up to 4 % by weight of a deflocculant and up to 10 % by weight of colloidal silica. Preferably, it further comprises from 0.5 to 4 % by weight of a deflocculant and from 0.5 to 10 % by weight of colloidal silica. Such a composition has a viscosity of between 9 to 12 Pa.s.

The invention also concerns a refractory component having an insulating coating.

- 15 The invention also concerns a process for coating a piece of refractory material used in the casting of molten metal, particularly steel with the composition of the invention.

According to this process:

- the piece is dipped at ambient temperature in a composition as described above for a time less than one minute;
- 20 - it is allowed to dry in the open air for 2-4 hours.

It is possible to produce several layers with the aid of this process.

- a first layer of slip is deposited on the piece by the first immersion;
 - the piece is allowed to dry in the open air for 45 minutes to 2 hours;
 - a second layer of slip is deposited on the piece by the second immersion;
- 25 - the piece is allowed to dry in the open air for 2-4 hours.

The material of the invention presents numerous advantages.

It is easier to apply than the papers and mats of ceramic fibers. Nor does it generate fibers dangerous for health.

- 30 With regard to the coatings previously known, it assures a better thermal insulation because its porosity is greater and because the portion of closed porosity, furnished by the insulating microspheres, is more substantial. Furthermore, thanks to the particular viscosity of the slip, the quality of the thermal insulation is improved because it is possible to deposit a greater coating thickness on the piece without impairing the insulation characteristics. This thickness can range up to 4 mm in a single layer and up to 7 mm in two layers.

- 35 Finally, it is readily possible to produce insulating pieces totally or partially of this material. Other characteristics and advantages of the invention will become evident from the following detailed description and the implementation examples.

Example I

- 40 A steel casting component, such as a nozzle, comprised of an elongated alumina-graphitized

body is coated with a coating of insulating refractory material. A slip in which the piece will be immersed is prepared for this purpose. To prepare the slip, an organic binder, e.g., dextrin, is dissolved in an appropriate amount of water. Dextrin is a polysaccharide that provides raw mechanical strength. It is also a viscosity agent. It is eliminated in place

5 during preheating of the piece.

A second binder is added, e.g. a clay of the kaolinite type. Clay is an agent for suspending, insulating microspheres and atomized silica grains. It also contributes to raw cohesion.

It is necessary to agitate the composition continuously during the addition of dextrin and clay in order to guarantee homogeneity, and particularly in the case of clay, to hydrate it completely and avoid its agglomeration into aggregates. This agitation, is obtained preferably by means of a planetary-type mixer, e.g., one of the COUVROT-LAINE brand. A deflocculant is then added, for example, of the type known under the commercial reference DOLAPIX CE 64, sold by the German company ZSCHIMMER & SCHWARZ. DOLAPIX is a dispersant/

15 deflocculant for raw materials and ceramic masses based on carboxylic acid without alkali, particularly destined for the deflocculation of ceramic oxides, steatites, etc.

Colloidal silica is added in the form of a liquid solution with 30 % colloidal silica and grains of atomized silica are introduced. These grains are obtained by pulverization of a silica slip in a stream of air. The liquid droplets in suspension in air have a size from 50 μm to 1.5 mm in diameter. By elimination of the water in a stream of hot air, more or less complete

20 microspheres of silica are obtained.

Finally, insulating microspheres, e.g., of alumina silicate and of a size between 5 and 500 μm are added. These microspheres are very light. The inherent density of the material

constituting them is between 2.7 and 2.8 g/cm^3 but, because these microspheres are hollow, the apparent density of the microspheres is only 0.6-0.8 g/cm^3 . These microspheres thus assure a very good thermal insulation. Naturally, as discussed above, it is necessary to continuously agitate the composition during the successive addition of each of the components.

The composition of the invention that has a viscosity of 12 Pa.s can be deposited on the piece by any appropriate method, e.g., by spattering. However, the application of the coating is preferably done by immersion.

30 The piece is immersed in the composition at a rate that can be relatively substantial (several meters per minute). The piece is kept immersed for less than 1 minute, e.g., 30 seconds.

The piece is withdrawn from the bath. The rate of withdrawal should be relatively slow, e.g., less than 3 meters per minute. The piece is then allowed to drain above the bath for less than 1 minute, e.g., some 30 seconds, then, it is allowed to dry in air. If only one layer is applied, the drying time in the open air will be 2-4 hours. If 2 or more layers are applied, the drying time in air is shorter, e.g., from 45 minutes to 2 hours before the application of the next layer. Finally, the last layer is allowed to dry for 2-4 hours as for a single layer coating.

40 The pieces can then be dried thoroughly in a kiln at a constant temperature of 120°C for one hour.

Example of the composition:

	Water	:	20.0 %
	Dextrine	:	3.2 %
	Colloidal silica	:	1.0 %
5	Dolapix CE 64	:	2.0 %
	Fillite SG 500	:	10.0 %
	Clay (HYMOD RF CLAY)	:	4.6 %
	Atomized vitreous silica grains	:	59.2 %

- 10 The chemical composition of the coating obtained from this composition, is as follows:

INGREDIENTS	% (BY WEIGHT)
SiO ₂	91.94
Al ₂ O ₃	6.32
TiO ₂	0.11
Fe ₂ O ₃	0.62
CaO	0.02
MgO	0.03
Na ₂ O	0.02
K ₂ O	0.13
Burning loss	0.56

The density of the coating obtained is less than 1.1, its specific weight is 1.5 to 2 g/cm³ and its porosity is 40 to 55 %.

15 Example II

A preheating sleeve is produced for a tundish stopper rod. The sleeve has a cylindrical part that fits on the outside diameter of the stopper rod and a flared internal part that completely covers the taphole of the distributor. This sleeve was made of the insulating refractory material of the invention by pouring a slip in a plaster mold.

20

Example III

A pouring spout cover plate was made for the glass industry. The plate is a parallelepiped having a thickness of 50 mm. This plate is made of the insulating refractory material of the invention by pouring in a plaster mold.

Claims.

1. Insulating refractory materials characterized in that it comprises from 20 to 80 % by weight of a ceramic matrix, from 5 to 40 % by weight of insulating microspheres, from 0.5 to 15 % by weight of one or more binders and up to 5 % by weight of water, said one or more binders conferring a viscosity higher than 8 Pa.s to the composition that is used in making said material.
2. Material according to claim 1, characterized in that the ceramic matrix comprises vitreous grains.
3. Material according to claim 2, characterized in that the vitreous grains comprises grains of silica, notably atomized silica.
4. Material according to any one of claims 1 to 3, characterized in that it further comprises up to 4 % by weight of a deflocculant.
5. Material according to any one of claims 1 to 4, characterized in that it further comprises up to 20 % by weight of colloidal silica.
6. Material according to any one of claims 1 to 5, characterized in that the insulating microspheres comprises hollow spheres of a material comprising silica and alumina.
7. Material according to claim 6, characterized in that the material comprising silica and alumina contains 55 to 65 % by weight of silica and 27 to 33 % by weight of alumina.
8. Material according to anyone of claims 1 to 7, characterized in that said one or more binders comprise an organic binder.
9. Material according to claim 8, characterized in that the organic binder comprises dextrine.
10. Material according to one of claims 1 to 9, characterized in that said one or more binders comprise a clay of the kaolinite type.
11. Piece, notably for the casting of molten metal having a body of refractory material, characterized in that this body has a coating of a material according to any one of claims 1 to 10.
12. Piece, notably for the casting of molten metal, characterized in that it is made entirely or partially of the refractory material of claims 1 to 10.
13. Process for preparing a composition for coating an article of refractory material used in the casting of steel, characterized in that:
 - one or more binders are dissolved in a quantity of water;
 - grains of vitreous silica, preferably atomized, are added while the solution is being

agitated, so as to hydrate them and to form a slip;

- microspheres of an insulating material are added while continuing to agitate the slip to render it homogeneous, characterized in that said binder provides a viscosity higher than 8 Pa.s to the slip.

- 5 14. Process according to claim 13, characterized in that a deflocculant is added after the addition of said one or more binders.
- 15 15. Process according to either claim 13 or 14, characterized in that colloidal silica is added before the addition of the vitreous silica.
- 10 16. Process for coating an article of refractory material used in the casting of molten metal, characterized in that:
 - the article is immersed at ambient temperature in a composition according to any one of claims 1 to 10 for less than one minute;
 - it is allowed to dry in the open air for 2 to 4 hours.
- 15 17. Coating process according to claim 16, characterized in that:
 - a first layer of slip is deposited on the article by a first immersion;
 - the article is allowed to dry in the open air for 45 minutes to 2 hours;
 - a second layer of slip is deposited on the article by a second immersion;
 - the article is allowed to dry in the open air for 2-4 hours.
- 20 18. Aqueous composition for the manufacture of an insulating refractory material comprising from 20 to 70 % by weight of a ceramic component, from 5 to 40 % by weight of isolating microspheres, from 0.5 to 20 % by weight of one or more binders and from 5 to 25 % by weight of water, said composition having a viscosity higher than 8 Pa.s.
19. Composition according to claim 18, characterized in that said ceramic component comprises gains of vitreous silica, preferably atomized silica.
- 25 20. Composition according to either claims 18 or 19, characterized in that said one or more binders comprise an organic binder.
21. Composition according to claim 20, characterized in that the organic binder comprises a polysaccharide.
- 30 22. Composition according to anyone of claims 18 to 21, characterized in that said one or more binders comprise a clay of the kaolinite type.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/BE 99/00073

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C04B35/66 C04B35/14 C04B38/08 C04B41/45

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C04B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category ²	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 4 874 726 A (DRESSER INDUSTRIES, INC.) 17 October 1989 (1989-10-17) column 1, line 57 - column 2, line 40; claims 1-4; table 1 ---	1-22
A	DE 196 27 961 A (VIESSMANN WERKE GMBH & CO) 15 January 1998 (1998-01-15) the whole document -----	1-22

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

3 August 1999

Date of mailing of the international search report

10/08/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Luethe, H

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/BE 99/00073

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 4874726 A	17-10-1989	AU 2478188 A	18-05-1989
		CA 1320504 A	20-07-1993
		DE 3838778 A	01-06-1989
		GB 2212491 A	26-07-1989
		JP 1160883 A	23-06-1989
<hr/>			
DE 19627961 A	15-01-1998	NONE	
<hr/>			